	CARATTERISTICHE PRINCIPALI - PRINCIPAL CHARACTERISTICS CARACTERISTIQUES PRINCIPALES - HAUPT EIGENSCHAFTEN	Date 04/04/2022 Edition 01

STROMBOLI

Caratteristica Characteristic Caractéristique Charakterdarsteller	Norma Norm Norme Norm	Tolleranza Tolerance Tolérance Toleranz	Dichiarato Declared Déclaré Deklariert
Peso (g/ml) – Weight (g/lm) Poids (g/ml) - Gewicht (g/lm)	EN 12127	± 5 %	380
Peso (g/m²) - Weight (g/m²) Poids (g/m²) - Gewicht (g/m²)	EN 12127	± 5 %	270
Altezza (cm) - Width (cm) Largeur (cm) - Breite (cm)	--------	± 2 %	140
Resistenza all'abrasione (cicli) Abrasion resistance (rubs) Résistance à l'abrasion (tours) Scheuerfestigkeit (Scheuertouren)	ISO 12947-2 (Martindale)	± 10 %	> 200.000
Solidità del colore alla luce (scala dei blu) Light fastness (blue scale) Solidité à la lumière (échelle des bleu) Lichtechtheit (Blaumaßstabe)	ISO 105-B02 (Xenotest)	da 5 a 8	6
Solidità del colore allo sfregamento (scala dei grigi) Fastness to rubbing (grey scale) Solidité au frottement (échelle des gris) Reibechtheit (Graumaßstabe)	ISO 105-X12 (Crockmeter)	da 4 a 5	4/5
Pilling (2000 cicli) - Pilling (2000 rubs) Pilling (2000 tours) - Pilling (2000 scheuertouren)	ISO 12945-2	da 4 a 5	5
Composizione Composition Composition Zusammensetzung	100% POLIAMMIDE RICICLATA ECONYL® 100% RECYCLED POLYAMIDE ECONYL® 100% POLYAMIDE RECYCLÉ ECONYL® 100% RECYCELTES POLYAMIDE ECONYL®		

Leggere differenze di colore tra un lotto e l'altro sono da considerarsi normali

Slight colour differences between one lot and another have to be considered within commercial tolerance

Légères différences de couleur entre un lot et l'autre doivent être considérés comme étant normales

Leichte Farbunterschiede sind zwischen zwei Partien als normal zu betrachten

Reazione al fuoco – Flammability - Classement au feu – Feuersicherung

Can meet	
UNI 9175 Class 1 IM EN 1021-1 & 2 BS 7176 Class Low Hazard California TB 117-2013	Altri test fuoco possono essere superati, il superamento di alcuni test fuoco può dipendere dalla schiuma utilizzata Will also pass other flammability standards. Flame retardant performance is dependent upon the foam used Autres tests feu peuvent être passés. La performance au feu dépend de la mousse utilisée Wird auch andere Brandschutzstandards erfüllen. Die flammhemmende Leistung ist anhängig von dem verwendeten Schaum

Manutenzione e lavaggio – Cleaning and washing – Nettoyage et lavage – Reinigung und waschen



ECONYL®

OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100 073313.O CENTROCOT Tested for harmful substances. www.oeko-tex.com/standard100

Global Recycled Standard
GRS Certified by ICEA
[GRS 2020-138]

GUARANTEE 5 YEARS