SPINNAKER

TECHNICAL DATA SHEET

Article:	**SPINNAKER**
Composition:	**92%CO-8%PA**
Width:	**140 cm +/- 3%**
Weight:	**542 gr/ml - 387 gr/sqm +/- 5%**
Repeat:	**warp 8 cm - weft 8,3 cm**
Abrasion Martindale:	**25000 cycles +/- 10%** **UNI EN ISO 12947-2:2000**
Care instructions:	
Pilling:	**grade 4 (change at 5000 turns)** **UNI EN ISO 12945-2:2002**
Dry clean fastness:	**Colour change 4-5** **UNI EN ISO D01:1995**
Rub fastness:	**Dry 4-5 / Wet 2-3 (Black WET 2)** **UNI EN ISO 105-X12:1995**
Light fastness:	**Light colour 4-5 / Medium-Dark colour 5** **UNI EN ISO 105-B02**
Flame resistance:	**BS 5852-1 (1979) CIGARETTE** **BS 5852:2006 CIGARETTE** **CAL TB 117:2013 FAIL*** **BS 5852-1 (1979) MATCH****
Flame resistance notes:	***CAL TB 117:2013 fail: SECTION 2. BARRIER MATERIALS TEST Upholstery cover fabrics that fail the cover fabric test described in Section 1 can be used in upholstered furniture if a barrier (interliner) material that passes this test method is used. When a barrier is required, the barrier material must cover all sides and top of the seating cushion(s). Exceptions: Non-reversible and non-detachable seating cushions do not require the use of the barrier material on the underside of the seating cushion.** ****BS5852-1 (1979) MATCH: Cover fabric containing at least 75% by weight of cotton, flax, viscose, modal, silk or wool, used separately or together and not coated with polyurethane or a polyurethane preparation. Cover fabric shall be used with a fire resistant interliner meeting the requirements of Shedule 3 of Statutory Instrument. In this situation, the CONFORMITY of Match Test according to Part I of Schedule 5 of Statutory Instrument IS NOT NECESSARY.**
Notes:	**In compliance with the "REACH" regulation**

TORRI LANA
1885